

IN THE CLAIMS:

The text of all pending claims, (including withdrawn claims) is set forth below. Cancelled and not entered claims are indicated with claim number and status only. The claims as listed below show added text with underlining and deleted text with ~~striketrough~~. The status of each claim is indicated with one of (original), (currently amended), (cancelled), (withdrawn), (new), (previously presented), or (not entered). Please AMEND claims 3, 5, 6, 9, 10 and 11 in accordance with the following:

1. **(Original)** A porous cellulose aggregate having a secondary aggregate structure formed by aggregation of primary cellulose particles, the aggregate having a pore volume within a particle of 0.265 cm³/g to 2.625 cm³/g, containing type I crystals, and having an average particle size of more than 30 µm and 250 µm or less, a specific surface area of 1.3-20 m²/g, a repose angle of 25° or more and less than 44° and properties to disintegrate in water.
2. **(Original)** The porous cellulose aggregate according to Claim 1, wherein the repose angle is 25° to 42°.
3. **(Currently Amended)** The porous cellulose aggregate according to Claim ~~1-or-2~~, wherein a breaking load of a tablet obtained by compressing 0.5 g of the porous cellulose aggregate at 20 MPa is 165 to 410 N.
4. **(Original)** The porous cellulose aggregate according to Claim 3, wherein the breaking load is 200 to 410 N and a disintegration time is 75 seconds or less.
5. **(Currently Amended)** A process for producing the porous cellulose aggregate according to ~~any one of Claims 1 to 4~~claim 1, comprising a step of drying a dispersion containing two or more groups of primary cellulose particles having different average particle sizes and a liquid medium wherein the cellulose dispersion particles have an average particle size of 1 to 110 µm.
6. **(Currently Amended)** A molded product composition comprising one or more active ingredients and the porous cellulose aggregate according to ~~any one of Claims 1 to 4~~claim 1.

7. **(Original)** The molded product composition according to Claim 6 wherein the one active ingredient is a poorly water-soluble active ingredient.

8. **(Original)** The molded product composition according to Claim 6 wherein the one active ingredient is a sublimable active ingredient.

9. **(Currently Amended)** A molded product composition comprising one or more active ingredients liquid or semisolid at normal temperature and the porous cellulose aggregate according to ~~any one of Claims 1 to 4~~claim 1.

10. **(Currently Amended)** A molded product composition comprising one or more active ingredients finely pulverized to a particle size of 40 μm or less and the porous cellulose aggregate according to ~~any one of Claims 1 to 4~~claim 1.

11. **(Currently Amended)** A molded product composition comprising one or more active ingredients finely pulverized to a particle size of 10 μm or less and the porous cellulose aggregate according to ~~any one of Claims 1 to 4~~claim 1.